Technical Data Sheet

DURALON UltraTec

Hydrophobic and Oleophobic Coating

SUMMARY

DURALON UltraTec is an innovative surface modification, by using fluorinated polyether, to create a durable, mono-molecular anti-smudge surface.

APPLICATIONS

DURALON UltraTec is the most effective for glass and Si02 coated surfaces.

- Ophthalmic lenses
- Optical lenses
- Optical filters
- Displays
- Mirrors
- Glass

FEATURES

DURALON UltraTec adds the following characteristics to the surface.

- Anti-smudge, reduction of dirt transfer to the surface
- Easy to clean, Improvement of cleanability
- Hydrophobic, improvement of water repellency
- Oleophobic, improvement of oil repellency
- Durability, abrasion resistant and protection against micro-scratches
- Low friction, improvement of surface smoothness
- Low refractive index, highly transparent in the visible spectrum
- Drop in solution for your process

GENERAL PHYSICAL PROPERTIES

PROPERTIES (*)	UNIT	DURALON UltraTec	Si02 STANDARD SURFACE
Contact angle of water	°	108-110	48
Surface tension	mN/m	13	54
Static friction coefficient (1)	-	0.1	0.25
Easy to clean performance	-	Good	Poor
Anti-fingerprint performance	-	Good	Poor
Abrasion resistance (2)	○	102-105	-

(*) Typical properties are not suitable for specification purposes

(1) Measured with cheese cloth

(2) Contact angle of water after 6,400 abrasion strokes with cotton cloth; weight load: 2.5 kg; stamp size: 15 mm x 25 mm; force: 0.66 kg / cm²; stamp hardness: 66A

APPLICATION METHODS

Dry application methods	PVD (Physical Vapor Deposition)
Wet application methods	Spray, Dip, Spin, Flow

DURALON UltraTec

Hydrophobic and Oleophobic Coating

CONTACT INFORMATION

COTEC GmbH
Frankenstraße 19
63791 Karlstein
Germany
Tel.: +49 6188 994 62 0
sales@cotec-gmbh.com

cotec-gmbh.com

SDC Technologies—Americas
Corporate Headquarters
800-272-7681 (Toll Free USA)
Tel.: +1-714-939-8300
technicalsupport.ca@sdctech.com

SDC Technologies—Europe
+44-1633-627030
technicalsupport.eu@sdctech.com

SDC Technologies—China
+86-21-61517768
customercare.cn@sdctech.com

SDC Technologies
Asia Pacific Pte. Ltd.
+65-6210-6355
customercare.ap@sdctech.com

©2026 COTEC GmbH All rights reserved. COTEC GmbH is a wholly-owned subsidiary of SDC Technologies, Inc. SDC Technologies is a wholly-owned subsidiary of Mitsui Chemicals, Inc.

Version 06/2021

PROCESS PARAMETERS

Standard process parameters available upon request

STORAGE AND HANDLING INSTRUCTIONS

Impregnated tablets for dry application methods (PVD):
Storage cool and dry between 4°C and 25°C; Shelf-life: 6 months
Warm up to room temperature before use

Liquid solution for dry application methods (PVD):
Storage cool and dry between 4°C and 6°C; Shelf-life: 6 months
Warm up to room temperature before use

Liquid solution for wet application methods (Spray, Spin, Dip, Flow):
Storage cool and dry between 4°C and 6°C
Warm up to room temperature before use

PACKAGING INFORMATION

Impregnated tablets for dry application methods (PVD):
Tablets are separately sealed with additional inert gas

Liquid solution for dry application methods (PVD):
Details upon request

Liquid solution for wet application methods (Spray, Spin, Dip, Flow):
Details upon request

HEALTH AND SAFETY INFORMATION

Before using this product, read and understand the Safety Data Sheet, SDS, which provides information on health, physical, and environmental hazards, handling precautions and first aid recommendations. For a copy of an SDS, contact a sales or customer service representative.

WARRANTY AND LIABILITY LIMITATIONS

Information contained herein is accurate to the best of our knowledge. The coating solution properties and cured coating properties listed herein represent typical values for DURALON UltraTec and are not meant as specifications. COTEC GmbH insists that users conduct their own tests for applicability and fitness for any purpose. Statements concerning use of products or formulations described herein shall not be construed as a warranty or license to infringe any patent or trademark, and no liability for infringement arising out of such use is assumed. Please refer to COTEC Terms and Conditions or to your Purchase Agreement with COTEC for the warranty coverage of COTEC's product.

PRODUCT SHIPPING AND AVAILABILITY

Typical lead-time for shipment of COTEC is depended on product ordered and is listed in confirmation of purchase order. COTEC provides several shipping options. Please contact an COTEC representative to determine which option best fits your needs.